

CUSTOMER SPECIFICATION

		Nominal	Minimum	Maximum	Test Methods
Thickness (micron)		50	42	58	COV-E-201
Width (mm)	0-179	any	ES		COV-E-200
	180-299		-3	+15	
	300-374		-4	+18	
	375-474		-5	+20	
	475-up		-6	+25	
			-8	+30	
Length (m)	0-299	any	-5	+15	COV-E-217
	300-499	any	-8	+20	
	500-799	any	-10	+25	
	800-up	any	-15	+30	
Width (mm)	0-179	any	TS		COV-E-200
	180-299		-3	+3	
	300-350		-5	+5	
	351-399		-5	+7	
	400-499		-6	+17	
	500-599		-8	+21	
	600-699		-10	+25	
	700-799		-11	+29	
	800-899		-13	+34	
	900-999		-15	+38	
	1000-1099		-17	+43	
	1100-1199		-18	+47	
	1200-1299		-20	+52	
	1300-1399		-22	+56	
	1400-1499		-24	+61	
	1500-1599		-26	+65	
	1600-1699		-28	+70	
1700-1800	-30	+74			
Length (m)	0-179	any	-3	+15	COV-E-217
	180-299	any	-4	+28	
	300-374	any	-5	+20	
	375-474	any	-6	+25	
	475-up	any	-8	+30	
Modulus (Kg/cm2)	LD	3000		3500	COV-E-212
	TD	2800		3400	
Elongation (%)	LD	140	80		COV-E-211
	TD	170	100		
Tensile (Kg/cm2)	LD	700	500		COV-E-211
	TD	500	300		
Shrink (%) at 85°C	LD	30	22		COV-E-209
	TD	38	30		
Haze (%)				7	COV-E-340
Gloss (g.u.)			80		COV-E-341
O ₂ (cm ³ / m ² ,24h,bar)	at 23°C, 0% RH	20		60	COV-E-342
CO ₂ (cm ³ / m ² ,24h,bar)	at 23°C, 0% RH			150	COV-E-343
TRANSPORTATION and STORAGE					
Recommended Temperature			2°C	26°C	
Recommended R.H				80%	
Recommended Storage period				12 Months	

NOTE

All statements or recommendations are based on data knowledge considered to be true and accurate at the time of printing but should be verified by the user. Since the condition of use are beyond our control we do not warrant the completeness or suitability for any intended purpose of any statement or recommendation, or the result to be obtained. Please read all the statements or recommendations in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods and services by us. National or local legal requirements relating to health safety at work and the protection of the environment shall be applicable in all cases.

VERSION: n° 6	DATE: 21-Jan-2022	ISSUED BY:  Jadranka Guy Customer Technical Documentation Administrator	APPROVED BY:  Andrzej Baran Executive Director Quality Europe
---------------	-------------------	---	--