

CUSTOMER SPECIFICATION

		Nominal	Minimum	Maximum	Test Methods
Thickness (micron)		56	50	62	COV-E-201
Bag patched (for single side bags)		173	140	204	
Width (mm) 0-179 180-299 300-374 375-474 475-up			ES		COV-E-200
			-3	+15	
			-4	+18	
	any		-5	+20	
			-6	+25	
			-8	+30	
Length (mm) 0-299 300-499 500-799 800-up		any	-0	+50	COV-E-217
Modulus (kg/cm²)	LD	2100	1600		COV-E-212
	TD	2100	1500		
Elongation (%)	LD	200	150		COV-E-211
	TD	180	110		
Tensile (kg/cm²)	LD	700	500		COV-E-211
	TD	750	550		
Shrink (%) at 85°C	LD	13	10		COV-E-209
	TD	17	13		
Haze (%)		25		35	COV-E-340
Gloss (g.u.)		85	75		COV-E-341
O₂ (cm³/ m²,24h,bar)	at 23°C, 0% RH	20		60	COV-E-342
CO₂ (cm³/ m²,24h,bar)	at 23°C, 0% RH			100	COV-E-343
<u>TRANSPORTATION and STORAGE</u>					
Recommended Temperature			2°C	25°C	
Recommended R.H				80%	
Recommended Storage period				12 Months	

NOTE

All statements or recommendations are based on data knowledge considered to be true and accurate at the time of printing but should be verify by the user. Since the condition of use are beyond our control we do not warrant the completeness or suitability for any intended purpose of any statement or recommendation, or the result to be obtained. Please read all the statements or recommendations in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods and services by us. National or local legal requirements relating to health safety at work and the protection of the environment shall be applicable in all cases.

VERSION: n° 4

DATE: 20-Jul-2023

ISSUED BY:

MOlek

Monika Olek

Customer Technical Documentation Administrator

APPROVED BY:

Baran

Andrzej Baran

Executive Director Quality Europe